

PRODUCT DATA SHEET

PRODUCER	PLASTIKA KRITIS SA
PRODUCT	KRITIFIL PE 1230

DESCRIPTION	multi-layer, colorless, silage, underlay film
RESIN(S)	LLDPE
NOMINAL THICKNESS (mic)	35
AVERAGE THICKNESS TOLERANCE	± 5% on nominal thickness
THICKNESS TOLERANCE AT ANY POINT	-20%

MECHANICAL PROPERTIES	TYPICAL VALUE	VARIATION	TEST METHOD
TENSILE STRENGTH AT BREAK (MPa)			
-MACHINE DIRECTION	25	- 5%	EN ISO 527-3
-TRANSVERSE DIRECTION	25	- 5%	EN ISO 527-3
ELONGATION AT BREAK (%)			
-MACHINE DIRECTION	500	- 5%	EN ISO 527-3
-TRANSVERSE DIRECTION	600	- 5%	EN ISO 527-3
TEAR RESISTANCE (MD) (gf/mic)	4	- 5%	ASTM D1922

Version 230228



We hereby certify that the product consigned as per the above, meets the standard manufacturing specifications, according to the plans established by our Quality System based on ISO 9001:2015.

P.O Box 1093, 711 10 Iraklion Crete Greece
Tel: +30 2810 308500 Fax: +30 2810 381328
Email: rnd@plastikakritis.com

LIMIT OF LIABILITY

PLASTIKA KRITIS warrants that this product conforms to its specifications. Buyer is responsible to verify the suitability of the product for the particular use. The amount of any claim against PLASTIKA KRITIS and PLASTIKA KRITIS' liability relative to the product's properties or performance, shall in no event exceed the purchase value of the product. In no event shall PLASTIKA KRITIS be liable for loss of profit or special, indirect or consequential damages.